



**LT XLPE CABLE**

TDS Doc.No:PIL/TE/250425/000052

DESIGN CODE : LVIS09AXSWYL003C006SA002S

Particulars	3 Core X 6 Sq.mm
Name of Manufacturer	Polycab India Ltd
Type of cable	A2XWY
Voltage Grade V	1100
No of cores X size in sqmm	3 Core X 6 Sq.mm
Conductor	
a) Material	H2/H4 Grade Aluminium as per Class 1 of IS: 8130/2013, latest
b) Max. d.c. resistance of conductor at 20° C (ohm/km)	4.61
c) Shape of the conductor	Solid Circular
Insulation	
a) Material	XLPE as per IS 7098(Pt-1)/88, Latest
b) Nominal thickness (mm)	0.7
c) Core identification	Red, Yellow, Blue
Inner Sheath	
a) Material	Extruded PVC Type ST2 as per IS:5831/84
b) Minimum thickness (mm)	0.3
Armouring	
a) Material	Galvanised Steel
b) Type of armouring	Round Wire
c) Nominal size of armour (mm)	1.400
d) Tolerance on armour dimensions	± 0.040 mm
Outer Sheath	
a) Material	Extruded FR-LSH PVC Type 'ST2' as per IS:5831/ 84
b) Thickness (mm)	1.24 (Min.)
c) Colour of sheath	Black
Electrical Parameters	
a) Max. a.c. resistance of conductor at 90° C (ohm/km)	5.91
b) Calculated Cable reactance (ohm/km)	0.0862

Format ID: TE/QMS/F/07, R-00, Date: 16/03/2025

c)	Impedance of cable (ohm/km)	5.91
d)	Approx. Cable Capacitance (mfd/km)	0.27
11.00		90°C
12.00		250°C
13.00		0.57
<b>Continuous Current carrying capacities :-</b>		
(a)	In Ground at 30°C (A)	46
(b)	In Air at 40°C (A)	42
Applicable Standard		IS 7098 Part I/88,IS 8130/2013,IS 5831/84, IS 3975/1999 etc. with latest up to date amendments
Approx. overall diameter of the cable in mm		15.0 +/- 2.0
Minimum bending radius		12 times Overall diameter
Max. Tensile strength		
(i)	for Cables pulled with stocking (Newtons)	9 x D <sup>2</sup> , D is the cable OD in mm
(ii)	for Cables pulled with pulling eyes (N)	540
Embossing		POLYCAB ELECTRIC 1100 VOLTS GRADE XLPE FR-LSH
Printing		YEAR POLYCAB ELECTRIC 1100 VOLTS GRADE XLPE FR-LSH CABLE SIZE CABLE TYPE WITH SEQUENTIAL MARKING at every one meter interval.
Standard Drum Length (Mtr.)		1000 Mtr. ±5%
Non- Standard Drum Length (Mtr.)		Maximum 5% of order quantity
<b>FR-LSH PROPERTIES</b>		
a)	Oxygen Index	Min. 29% as per ASTM D- 2863
b)	Temperature Index	Min. 250 Deg.C as per ASTM D- 2863
c)	Smoke Density Rating	Max. 60% as per ASTM D- 2843
d)	Acid Gas Generation	Max. 20% as per IEC- 754- 1
e)	Flammability Test	As per IEC:332-I