



LT XLPE CABLE

TDS Doc.No:PIL/TE/250425/000453

DESIGN CODE : LVIS09AXSWYL004C035SA003S

Particulars	4 Core X 35 Sq.mm
Name of Manufacturer	Polycab India Ltd
Type of cable	A2XWY
Voltage Grade V	1100
No of cores X size in sqmm	4 Core X 35 Sq.mm
Conductor	
a) Material	H2/H4 Grade Aluminium as per Class 2 of IS: 8130/2013, latest
b) Max. d.c. resistance of conductor at 20° C (ohm/km)	0.868
c) Shape of the conductor	Stranded Compacted Sector
Insulation	
a) Material	XLPE as per IS 7098(Pt-1)/88, Latest
b) Nominal thickness (mm)	0.9
c) Core identification	Red, Yellow, Blue, Black
Inner Sheath	
a) Material	Wrapping of Tapes
b) Minimum thickness (mm)	0.3
Armouring	
a) Material	Galvanised Steel
b) Type of armouring	Round Wire
c) Nominal size of armour (mm)	1.60
d) Tolerance on armour dimensions	± 0.045 mm
Outer Sheath	
a) Material	Extruded FR-LSH PVC Type 'ST2' as per IS:5831/ 84
b) Thickness (mm)	1.40 (Min.)
c) Colour of sheath	Black
Electrical Parameters	
a) Max. a.c. resistance of conductor at 90° C (ohm/km)	1.11
b) Calculated Cable reactance (ohm/km)	0.0787

Format ID: TE/QMS/F/07, R-00, Date: 16/03/2025

c) Impedance of cable (ohm/km)	1.11
d) Approx. Cable Capacitance (mfd/km)	0.5
Maximum conductor temperature under normal operating conditions	90°C
Maximum conductor temperature at the termination of short circuit	250°C
Short Circuit rating of conductor for the duration of 1 sec (kA)	3.31
Continuous Current carrying capacities :-	
(a) In Ground at 30°C (A)	114
(b) In Air at 40°C (A)	114
Applicable Standard	IS 7098 Part I/88, IS 8130/2013, IS 5831/84, IS 3975/1999 etc. with latest up to date amendments
Approx. overall diameter of the cable in mm	27.0 ± 2.0
Minimum bending radius	12 times Overall diameter
Max. Tensile strength	
(i) for Cables pulled with stocking (Newtons)	9 x D ² , D is the cable OD in mm
(ii) for Cables pulled with pulling eyes (N)	4200
Embossing	POLYCAB ELECTRIC 1100 VOLTS GRADE XLP FR-LSH
Printing	YEAR POLYCAB ELECTRIC 1100 VOLTS GRADE XLPE FR-LSH CABLE SIZE CABLE TYPE WITH SEQUENTIAL MARKING at every one meter interval.
Standard Drum Length (Mtr.)	500 ± 5%
Non- Standard Drum Length (Mtr.)	Maximum 5% of order quantity and Min Individual Non-Standard Drum 200 meters
FR-LSH PROPERTIES	
a) Oxygen Index	Min. 29% as per ASTM D- 2863
b) Temperature Index	Min. 250 Deg.C as per ASTM D- 2863
c) Smoke Density Rating	Max. 60% as per ASTM D- 2843
d) Acid Gas Generation	Max. 20% as per IEC- 754- 1
e) Flammability Test	As per IEC:332-I