



LT XLPE CABLE

TDS Doc.No:PIL/TE/250425/002672

DESIGN CODE : LVIS09CXSWYL003C1.5SA001S

Particulars	3 Core X 1.5 Sq.mm
Name of Manufacturer	Polycab India Ltd.
Type of cable	2XWY
Voltage Grade V	1100
No of cores X size in sqmm	3 Core X 1.5 Sq.mm
Conductor	
a) Material	Plain annealed Copper as per Class 2 of IS:8130/2013
b) Max. d.c. resistance of conductor at 20° C (ohm/km)	12.1000
c) Shape of the conductor	Stranded Circular
Insulation	
a) Material	XLPE as per IS 7098(Pt-1)/88, Latest
b) Nominal thickness (mm)	0.7
c) Core Identification	Red, Yellow and Blue
Inner Sheath	
a) Material	Extruded PVC Type ST2 as per IS:5831/84
b) Minimum thickness (mm)	0.3
Armouring	
a) Material	Galvanised Steel
b) Type of armouring	Round Wire
c) Nominal size of armour (mm)	1.400
d) Tolerance	+/- 0.040
Outer Sheath	
a) Material	Extruded FR-LSH PVC Type ST2 as per IS:5831/84
b) Thickness (mm)	1.24 (Min.)
c) Colour of outer sheath.	Black
Electrical Parameters	
a) Max. a.c. resistance of conductor at 90° C (ohm/km)	15.4000
b) Calculated Cable reactance (ohm/km)	0.1050

c) Impedance of cable (ohm/km)	15.4000
d) Approx. Cable Capacitance (mfd/km)	0.18
Maximum conductor temperature under normal operating conditions	90°C
Maximum conductor temperature at the termination of short circuit	250°C
Short Circuit rating of conductor for the duration of 1 sec (kA)	0.21
Continuous Current carrying capacities :-	
(a) In Ground at 30°C (A)	26
(b) In Air at 40°C (A)	23
Applicable Standard	IS 8130/2013, IS 7098 Part I/88, IS 5831/84, IS 3975/1999 etc. with latest up to date amendments
Approx. overall diameter of the cable in mm	13.0 ± 2.0
Minimum bending radius	12 times Overall diameter
Max. Tensile strength	
(i) for Cables pulled with stocking (Newtons)	9 x D ² , D is the cable OD in mm
(ii) for Cables pulled with pulling eyes (N)	225
Embossing	POLYCAB ELECTRIC 1100 VOLTS GRADE XLPE FR-LSH
Printing	YEAR POLYCAB ELECTRIC 1100 VOLTS GRADE XLPE FR-LSH CABLE SIZE CABLE TYPE WITH SEQUENTIAL MARKING at every one meter interval.
Standard Drum Length (Mtr.)	1000 ± 5%
Non- Standard Drum Length (Mtr.)	Maximum 5% of order quantity
FR-LSH PROPERTIES	
a) Oxygen Index	Min. 29% as per ASTM D- 2863
b) Temperature Index	Min. 250 Deg.C as per ASTM D- 2863
c) Smoke Density Rating	Max. 60% as per ASTM D- 2843
d) Acid Gas Generation	Max. 20% as per IEC- 754- 1
e) Flammability Test	As per IEC:332-I